


DESCRIPTION


Project Name:	Barrio oeste vi
Section Name:	Muro medianero 42-41
Sensor Name:	Muro medianero
Location:	
Tagged By:	
Pouring Time:	06/16/2017 2:25 PM
Mix ID:	HB20-90-20-14Readymix
Maturity Method:	Temperature Time Factor
Datum Temperature:	0.0°C
Calibration coefficient:	a= -81.69 b= 39.86
Comments:	Se instala 15 cm bajo el espesor de la losa




TEST RESULTS

Max Temperature:	16.8 °C
Min Temperature:	4.2 °C
Maturity Index:	900 °C-hrs
Strength:	36.1 MPa


TEMPERATURE



MATURITY



STRENGTH



signature